

TIASA - Thermal Insulation Association of Southern Africa

Thermal Insulation – The Invisible Energy Saver !



TIASA GUIDE TO LEVELS OF TYPICAL INSULATION PRODUCTS TO ACHIEVE DEEMED-TO-SATISFY RULE FOR ENERGY EFFICIENCY IN A NON-VENTILATED ROOF AND CEILING CONSTRUCTION (SANS 204) & A SYSTEM OPTION WITH A RADIANT BARRIER OVER RAFTERS



Climatic Zones	1	2	3	4	5	6
Minimum required Total R-Value (m ² .K/W) (for roof solar absorptance of more than 0.55)	3.7	3.2	2.7	3.7	2.7	3.5
Direction of heat flow	Up	Up	Down and Up	Up	Down	Up
Estimated Total R-Value (m ² .K/W) of roof and ceiling materials (Roof covering & plasterboard only)	0.35 - 0.40			0.41 - 0.53		0.35 - 0.40
Estimated Minimum added R-Value of Insulation (m ² .K/W)	2.30 - 3.35			2.17 - 2.29		2.80 - 3.15

Generic Insulation Products		Density Kg/m ³	Thermal Conductivity W/(m.k.)	Example: Roof construction description: metal/tile roof 22° - 45° pitch with horizontal ceiling. DTS - Recommended deemed-to-satisfy min thickness (mm) of bulk insulation product only; or RB: System option with addition of Radiant Barrier over rafters - approx. (mm) of bulk insulation required											
				DTS		RB		DTS		RB		DTS		RB	
				Product	System	Product	System	Product	System	Product	System	Product	System	Product	System
1	Cellulose Fibre Loose-Fill	27.5	0.040	135	100	115	95	100	70	135	100	100	65	130	100
2	Flexible Fibre Glass Blanket	10-18	0.040	135	100	115	95	100	70	135	100	100	65	130	100
3	Flexible BOQ Polyester Fibre Blanket	24	0.038	130	95	110	90	90	65	130	95	90	60	125	100
4	Flexible Polyester Blanket	11.5	0.046	160	120	140	100	120	80	160	120	110	75	150	120
5	Flexible Mineral/Rockwool	60-120	0.033	115	85	100	80	80	75	115	85	80	55	100	90
6	Flexible Ceramic Fibre	84	0.033	115	85	100	80	80	75	115	85	80	55	100	90
7	Rigid Expanded Polystyrene (EPS)SD	15	*0.035	120	90	100	80	90	60	120	90	80	55	115	95
8	Rigid Extruded Polystyrene (XPS)	32	*0.028	100	70	80	65	70	50	100	70	65	45	90	75
9	Rigid Fibre Glass Board	47.5	0.033	115	85	100	80	80	55	115	85	80	55	100	90
10	Rigid BOQ Polyester Fibre Board	61	0.034	115	90	100	80	80	60	115	90	80	55	110	90
11	Rigid Polyurethane Board	32	*0.025	85	60	70	60	60	45	85	60	60	40	80	65

The grey (RB) columns above indicates the reduced DTS thicknesses of bulk insulation required if a radiant barrier is installed over the rafters.

(*)Thermal efficiencies are dependent on materials thickness, density, age, operating temperature and moisture.

Notes: (1) Thermal Conductivity used for calculation of recommended thicknesses of typical insulation materials as per TIASA Protocol for routine product testing for non-ventilated roof and ceiling constructions. Thermal efficiencies are dependent on materials thickness, density, age, operating temperature and moisture. These are apparent values and the estimated uncertainty is between 10% - 15%. Thicknesses rounded-off to nearest production standard. This is a guideline for general design purposes & rational design is always an option.

(2) The aforementioned deemed-to-satisfy recommended levels of insulation could be achieved by the use of reflective foils, bulk insulation or rigid board insulation or in combination with one another. Maximum efficiency may be achieved at reduced thicknesses taking the aforementioned into account. Careful consideration should be given to climatic zones which is prone to high humidity. Refer "The Guide to Energy Efficient Thermal Insulation in Buildings" page 58.

(3) Actual R-Values for roof construction systems are established through testing in accordance with ASTM C1363 Standard Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus with SAFIERA. Specifiers are encouraged to obtain these test results.

(4) Fire & safety: Refer SANS 10400 Part T Fire Protection – Insulation materials shall be tested and classified in accordance with SANS 428.

Climatic Zone	Roof & Ceiling Total System R-Value (m ² .K/W)	External Non-masonry Walls Total R-Value (m ² .K/W)	Floor Insulation R-Value (m ² .K/W) Under in slab heating	Pipe Insulation Internal Ø of pipe ≤ 80mm R-Value (m ² .K/W)	Pipe Insulation Internal Ø of pipe > 80mm R-Value (m ² .K/W)	Geysers Incl. of geyser Insulation
1	3.7	2.2	1	1	1.5	2
2	3.2	1.9	1	1	1.5	2
3	2.7	1.9	1	1	1.5	2
4	3.7	1.9	1	1	1.5	2
5	2.7	1.9	-	1	1.5	2
6	3.5	2.2	1	1	1.5	2
	See above	Thickness mm	Thickness mm	Thickness mm	Thickness mm	Thickness mm
		2	1	1	1	2
		3	1	1	1	2
		4	1	1	1	2
		5	-	1	1	2
		6	1	1	1	2
		EPS = 80	EPS = 35	EPS = 35	EPS = 55	Fiber G = 80 Fiber P = 95
		Fiber G = 100	Fiber G = 40	Fiber G = 40	Fiber G = 60	
		Fiber P = 100	Fiber P = 50	Fiber P = 50	Fiber P = 70	
		PU Foam = 55	PU Foam = 25	PU Foam = 25	PU Foam = 25	
		XPS = 65	XPS = 30	XPS = 30	XPS = 45	



Insulation - The invisible energy saver



By adding just 1% to your total building cost, you can install state of the art insulation.

The result:

- comfortable surroundings
- saving money on energy costs
- supporting a sustainable environment

CORPORATE MEMBERS



Administered by
AAAAASA
Group



Contact our members for products and services that meet the requirements of quality, performance and safety as set by the Thermal Insulation Association of Southern Africa (TTASA).

For a comprehensive list of Insulation Contractors, Distributors, Manufacturers, Suppliers & Specialists please visit: www.tiasa.org.za
Office: [011] 805 5002.